

Product Data and Test Information

PROTECTOSIL® 100

100% SILANE WATER REPELLENT

PRODUCT DESCRIPTION

Protectosil® 100 is a clear, penetrating, breathable, reactive penetrating sealer for use on concrete. It is a solvent-free, isobutylalkoxysilane. It allows for faster dry times and superior performance on high quality mix designs. It creates a hydrophobic layer that prevents water and waterborne contaminants from entering the substrate and causing premature deterioration.

ADVANTAGES

- Excellent resistance to chloride ion ingress
- 100% Moisture vapor transmission
- Dry time 15-45 minutes between 50°F - 100°F (10°C - 38°C)
- Mitigation of AAR & ASR deterioration
- Deep penetration into substrate
- No change in surface appearance or surface friction after application
- High resistance to alkali attack
- Long service life, reapplication between 10-20 years.
- Excellent performance on wearing surfaces
- Will not inhibit adhesion of paints and line striping
- Can qualify for LEED Credits



Protectosil® 100 shows excellent depth of penetration into concrete substrates, as well as preventing water and chloride ingress on treated surfaces.

PRECAUTIONS

- Not intended for below grade waterproofing.
- Not to be applied if the surface temp is below 20°F (-7°C) or above 110°F (43°C)
- Not to be applied if there is rain expected within 4 hours after application.
- Must be applied with proper ventilation. In an enclosed area an air respirator must be used.
- Not to be applied near heat, sparks, open flame, or other ignition sources.
- Close containers when not in use.

PREPARATION

Before application, concrete must be cured to a minimum of 80% compressive strength or to less than 8% moisture content. Concrete repair and any replacements must be completed prior to application of **Protectosil® 100**. Patching materials, caulking, sealing materials and traffic paint must be fully cured before application. All surfaces must be fully cleaned using power-washing, sandblasting, or chemical detergents of any surface contaminants (dirt, salt, laitance, paint etc.) and curing compounds.

Please confirm with your Protectosil® representative to verify the surface preparation is adequate. Always consult the full label and SDS for any precautionary safety measures before use and application. Use appropriate safety equipment and job site controls during application and handling.

COVERAGE RATES

Precast Concrete: 175-250 sq.ft./gallon

Cast-In-Place Concrete: 150-200 sq.ft./gallon

*Note: Coverage rates may vary by substrate porosity.

(continued)

APPLICATION

Protectosil® 100 should be applied using low-pressure pumping equipment with a wet fan type spray nozzle. Do not alter or dilute the material. Do not apply to a wet or damp substrate. This product should not darken or discolor the substrate if used at the recommended coverage rates, but due to variations in surface porosity and environmental conditions, applying a test patch is advised to verify desired results.

A flood application of the material is required. On horizontal surfaces, the liquid material shall pond on the surface at least 5 seconds before being absorbed. Once applied, traffic must be kept off the treated surfaces until an hour after the treated surface has completely dried. On vertical surfaces, the liquid material should be applied bottom up, and shall run down 6-8 inches below the spray.

TECHNICAL DATA

Color	water white
Active Ingredient	100% isobutylalkoxysilane
Solvent	none
Flash point	103°F
Density	7.8 lb/gal
VOC	<350g/L

TEST DATA

ASTM C642 "Water Absorption of Concrete"	
24 hours	0.49%
48 hours	0.50%
ASTM C672 "Deicer Scaling"	
100 Cycles (non-air-entrained concrete)	0 rating
AASHTO T259 "90 Day Salt Ponding"	
Non Abraded specimen ½" to 1"	94% reduction*
ASTM D6489 "Water Absorption of Concrete"	
48 hours	97% reduction
Penetration, OHD L-40	
Concrete 0.42 w/c ratio	¾ to ½ in

TEST DATA

NCHRP #244 Series II - Reduction in water absorption	
@ 150 ft ² /gal	88%
NCHRP #244 Series II - Reduction in chloride ion ingress	
@ 150 ft ² /gal	88%
NCHRP #244 Series IV - Reduction in chloride ion	
@ 150 ft ² /gal	99%

TECHNICAL SERVICE

Technical service engineers and scientists are available to answer questions. You can speak to one of our scientists directly by calling **732-289-1239**.

MANUFACTURER

Evonik Corporation

2 Turner Place
Piscataway, NJ 08854
1 (800) 828-0919
protectosil@evonik.com
evonik.click/protectosil

PROTECTOSIL® PRODUCTS ARE MANUFACTURED AT THE EVONIK CORPORATION THEODORE, ALABAMA, PLANT UNDER A QUALITY SYSTEM CERTIFIED TO ISO-9001, ISO-14001, AND ISO-50001 REQUIREMENTS.

For more information, SDS and the most updated product information, and to find your local representative, go to evonik.click/protectosil

Protectosil® = registered trademarks of Evonik Industries This information and all technical and other advice are based on Evonik Corp's ("Evonik") present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESSOR IMPLIED, AND SHALL HAVE NO LIABILITY FOR MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility and obligation to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.